

## XG81011

<b>Description</b>	Flexible opaque PVC extrusion compound
<b>Application</b>	Extrusion
<b>Form</b>	Granules
<b>Safety Data Sheet</b>	0

### Properties

(These values do not form part of a specification)

	<u>Units</u>	<u>Typical Results</u>
<b>Density</b>	kg/m <sup>3</sup>	1650
<b>Shore "A" Hardness</b>	Shore "A"	92
<b>BS Softness</b>	BSS	18

### Processing Conditions

Customers are recommended to determine optimum conditions for themselves as these will vary with each particular type of machine. As a general guide, typical temperatures are as follows:

	Zone 1	Zone 2	Zone 3	Zone 4	Die
<b>Barrel Temperature °C</b>	155	155	155	160	165

**Issue 1**

**June, 2016**

*Information in this publication and otherwise supplied to users is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given, nor is to be implied with respect of such information. Users should make their own enquiries to determine the suitability of products for any particular application. Freedom from patents, copyright and registered designs cannot be assumed*

INEOS Compounds Aycliffe Limited  
Registered in England No. 8651343  
Registered Office  
INEOS Compounds Aycliffe Limited  
School Aycliffe Lane  
Newton Aycliffe  
Co Durham  
DL5 6EA  
VAT No. 170 9349 92